




















Technical information (04/2021)

GRAVIHEL PUR TOPCOAT 430 STRUCTURE BLACK

- Two-component single layer structure coating with extreme weather, chemical, UV and mechanical resistance.
- Used in the protection of construction, agricultural machinery, rail vehicles, different steel constructions, PV and LCV (vans, trucks, campers) and for industrial varnishing, which requires high level of mechanical, chemical and weather resistance.
- For special effects you can add to any shade 10-20 % of GRAVIHEL Silver Pastes (21, 22 or 23), in order effect would be more visible we recommend to use GRAVIHEL 22 coarse silver or GRAVIHEL 23 extra coarse silver.
- VOC compliant

SUBSTRATE	SUBSTRATE PREPARATION		
	 P220 – P280	 GRAVIHEL Antisilicone cleaner	
	 GRAVIHEL Antisilicone cleaner	 P220 – P280	 GRAVIHEL Antisilicone cleaner
	 GRAVIHEL Antisilicone cleaner	 P220 – P280	 GRAVIHEL Antisilicone cleaner
	GRAVIHEL PUR WOOD PRIMER	 P360 – P600	Dust free
	 GRAVIHEL Antisilicone cleaner		
	 GRAVIHEL IND Plastic cleaner	 P500 – P800	 GRAVIHEL IND Plastic cleaner

Typ of product: Acryl – isocyanate (polyurethane)
Appearance: SEMI GLOSS
Delivery viscosity: Thixotropic
 DIN 53211 Φ4 / 20°C

Helios TBLUS d.o.o., Količevo 65, 1230 Domžale Slovenia
 T: + 386 1 722 40 00, E: office@helios-refinish.com, www.helios-refinish.com

1 / 3

Density of component A: 1,3 – 1,4 kg/l

Solid content: By volume: 62%

By weight: 71%

VOC: 2004/42/II B(e)(840)400

EU limit value VOC for this type of product (category II B (e)) in the form, which is ready for application is

840 g/l. VOC of this product, prepared for use is 400 g/l

IT IS ALSO USED TO RENOVATE INDUSTRIAL AND COMMERCIAL VEHICLES






Theoretical yield: 5 – 7,5 m²/lit.



Temperature resistance Short-term: up to 140 °C

(dry temperature) Long-term: up to 80 °C

Processing temperature: +10°C till max. +40°C, max.Humidity 75%

Color shades: Black

	Mixing ratio by Volume:	5:1 + 5% GRAVIHEL 2K PUR SINGLE COAT HARDENER GRAVIHEL THINNER ESS															
	Mixing ratio by Weight:	6:1 + 5% GRAVIHEL 2K PUR SINGLE COAT HARDENER GRAVIHEL THINNER ESS															
	Pot life of the mixture at 20°:	4 h															
	Viscosity (RFU): DIN 53211 φ4 / 20°C	Thixotropic															
	Application with spray gun:	1,5 – 1,8 mm 2 – 3 bar															
	Number of layers: Film thickness:	2 100 μm															
	Flash-off:	15 min. /20°C between coats															
	Drying time:	<table border="0"> <tr> <td>Object temperature</td> <td>at 20°C</td> <td>at 60°C</td> </tr> <tr> <td>Powder dry:</td> <td>30 min.</td> <td>-</td> </tr> <tr> <td>Dry to touch:</td> <td>5 h</td> <td>-</td> </tr> <tr> <td>Dry to assembly:</td> <td>8 - 10 h</td> <td>30 min.+ 1h/20°C</td> </tr> <tr> <td>Through dry:</td> <td>24 h</td> <td>30 min.+ 3h/20°C</td> </tr> </table>	Object temperature	at 20°C	at 60°C	Powder dry:	30 min.	-	Dry to touch:	5 h	-	Dry to assembly:	8 - 10 h	30 min.+ 1h/20°C	Through dry:	24 h	30 min.+ 3h/20°C
Object temperature	at 20°C	at 60°C															
Powder dry:	30 min.	-															
Dry to touch:	5 h	-															
Dry to assembly:	8 - 10 h	30 min.+ 1h/20°C															
Through dry:	24 h	30 min.+ 3h/20°C															
	Drying time (infra-red short-wave):	8 - 12 min. Distance to the object: 70 - 80 cm															

	Application with Airmix:	0 - 5% GRAVIHEL THINNER ESS Nozzle: 0,33 – 0,50 mm Pressure: 150 bar Flash-off between coats: 5 - 10 min. /20°C
	Shelf life:	2 years

FOR PROFESSIONAL USE ONLY - See Safety Data Sheet

2K materials react with humidity; take care that all containers and tools are absolutely dry. While coating, the ambient relative humidity should not exceed 80%.

The data may vary under various conditions.,

Any part of this information may change at any time without notice.

The information was derived from years of experience in the collaboration of Development and Technical Services and is the property of HELIOS Refinish. We guarantee that the quality of work carried out according to our instructions delivers results while we disclaim any liability if any other products were used or if other factors influenced the final appearance.

The latest version of TDS supersedes all previous versions. You can obtain the latest version from general distributor in your country.